

## PATENT ABSTRACTS OF JAPAN

(11)Publication number : 2003-022716

(43)Date of publication of application : 24.01.2003

(51)Int.Cl.

H01B 9/00

H01B 3/44

H01B 7/02

(21)Application number : 2001-208515

(71)Applicant : FURUKAWA ELECTRIC CO LTD:THE

(22)Date of filing : 09.07.2001

(72)Inventor : TANAKA TOSHIYA

## (54) INSULATING POWER CABLE MADE OF CROSSLINKED POLYETHYLENE

## (57)Abstract:

**PROBLEM TO BE SOLVED:** To provide an insulating power cable made of crosslinked polyethylene, which can be manufactured at a low price, and in which  $\tan \delta$  in a high temperature/high electric field is reduced.

**SOLUTION:** This is the insulating power cable made of crosslinked polyethylene wherein the insulator layer is composed of a crosslinked material of a resin composition in which 0.2 to 0.5 parts by weight of antioxidant prepared by mixing bis[2-methyl-4-(3-n-alkylthiopropionyloxy)-5-t-butylphenyl] sulfide 95 to 80 wt.% and 4,4'-thiobis (3-methyl-6-t-butylphenol) 5 to 20 wt.% are compounded against 100 parts by weight of polyethylene, and wherein grafting rate of bis[2-methyl-4-(3-n-alkylthiopropionyloxy)-5-t-butylphenyl] sulfide component to the polyethylene is 75% or more in its crosslinked material.

## LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]

Copyright (C); 1998,2003 Japan Patent Office